

Technical Data Sheet

Green plastic PPBH-CR04T

Biobased Compound for Injection Moulding

Description:

Green plastic PPBH-CR04T is made from 30-35% bran and rice husk. It is formulated from agricultural by-product. PPBH-CR04T for injection molding process with high flow and good stiffness characteristic. It is suitable for the production of general part, office stationery, household & personal care products etc.

Typical Material Properties:

PROPERTIES	TEST METHOD	UNIT	VALUES
Physical			
Biobased Carbon Content	ASTM D6866	%	30
Color	-	-	Slightly yellow to Beige (Textured)
Specific Gravity	ASTM D792	g/cm ³	1.03 – 1.12
Melt Flow Rate (230°C / 2.16 kg)	ASTM D1238	g/10 min	11
Water Absorption	ASTM D570	%	2.0 – 3.0
Mould Shrinkage	In-house Method	%	1.0 – 2.0
Mechanical			
Tensile Strength	ASTM D638	MPa	20
Elongation at Yield	ASTM D638	%	7
Flexural Modulus	ASTM D790	MPa	1145
Flexural Strain at Break	ASTM D790	%	9
Izod Impact Strength (Notched)	ASTM D256	J/m	33
Thermal			
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	98

Version: 00, Revision date: 30/01/2024

Technical Data Sheet

Green plastic PPBH-CR04T

Biobased Compound for Injection Moulding

Processing Technique:

Green plastic PPBH-CR04T in pellet form is recommended to be stored in properly sealed moisture barrier packaging at dry condition and away from sun light.

PARAMETER	UNIT	TYPICAL VALUE
^a Drying Temperature	°C	80
^a Drying Time / Moisture Content before moulding	Hours / %	4-6 / 0.1
^b Melt Temperature during processing	°C	180-230
Mould temperature range	°C	40-60

- ^a Preheat **Green plastic** compound preferably in a de-humidifying dryer for at least 4 hrs at 80 °C or until the moisture content is less than 0.1% prior to molding.
- ^b It is recommended to purge the barrel and **DO NOT** allow **Green plastic** to stay in the barrel for too long to prevent degradation of **Green plastic** in the event that process needs to stop for some time.

Version: 00, Revision date: 30/01/2024